

Epo Shield 110

Clear, high gloss, solvent free epoxy top coat system

DESCRIPTION

Epo Shield 110 is a clear or coloured, two component high build, high gloss, solvent free, epoxy roll coat wall and flooring system designed to be used as a high performance epoxy for decorative floors.

PRODUCT FEATURES & BENEFITS

- Non-flammable
- 100% solids epoxy (**Meets "Green Star" Building low VOC requirements**)
- Low yellowing
- Excellent adhesion qualities
- Negligible odour
- Adheres to most substrates including brick, masonry, compressed fibre board and timber
- Provides a high gloss finish

TYPICAL APPLICATIONS

As a high performance clear coating for decorative flooring.

VOC RATING

TESTED UNDER THE REQUIREMENTS OF:

IEQ 13 VOLATILE ORGANIC COMPOUNDS "GREEN STAR TECHNICAL MANUAL".

TVOC's calculated as the sum total of the VOC's of each individual raw material component.

The total VOC is	White or Colour	92.44 grams/ litre of ready to use product.
	Clear	92.44 grams/ litre of ready to use product.

APPLICATION RATES

Decorative floor finishes 6-8m²/litre/coat.

PACK SIZES

Epo Shield 110 is available in 10ltr containers.

PERFORMANCE PROPERTIES

APPEARANCE	FREE FLOWING LIQUID
COLOUR	CLEAR OR COLOURED
FINISH	GLOSS
VOLUME SOLIDS	100%
WEIGHT SOLIDS	100%
SPECIFIC GRAVITY	APPROX 1.05 @ 25°C
RE-COAT TIME	OVERNIGHT AT 25°C, 50%RH
POT LIFE	APPROX 40 MINUTES @ 25°C
VISCOSITY	APPROX 1000cps
FULL CURE	7 DAYS @ 25°C/50%RH
MIXING RATIO	3:1 BY VOLUME

Epo Shield 110

Clear, high gloss, solvent free epoxy top coat system

PREPARATION

- All surfaces to be coated must be structurally sound and free of all previous coatings, adhesives, efflorescence or laitance by abrasive blasting, high pressure water blasting, mechanical scrubbing or other means.
- All surfaces to be coated must be free of all dirt, grease, oil or other surface contaminants.
- All holes, non-structural cracks and surface deformities should be repaired prior to the application of Epo Shield 110.
- Ensure recoat times are adhered to between applications, a minimum of 12 hours is required between coats at temperatures above 25°C.

MIXING

1. Mixing should be by means of mechanical forced action mixer with a high speed shear stirrer.
2. First premix each individual component to form a homogeneous paste.
3. Join 3 parts, Part A RESIN with 1 part, Part B, mixing thoroughly for a minimum of 5 minutes until a homogeneous paste is obtained.
4. Avoid trapping air during the mixing process as this may cause pin holing in the coating during application.
5. Only mix as much product as can be used within the pot life of the product.

PLACING

1. Apply in a uniform manner using a brush, roller or airless sprayer, ensure application rates are adhered to and ensure all surface voids are filled.
2. Avoid pin holing.
3. Successive coats should be applied at right angles to the previous coats.
4. Epo Shield 110 is a minimum 2 coat system, including over Epo Flake.
5. It is recommended during application that the coating depth be tested at random points with a wet film gauge/comb.
6. Where a textured surface is required, broadcast appropriate crushed glass mixture on to the first coat while it is still tacky, allow to cure for 12 hours.
7. Once cured remove excess broadcast material using a broom or industrial strength vacuum.
8. Apply the second coat at right angles to the first.
9. Allow the surface to cure for a minimum of 24 hours before subjecting to pedestrian traffic, allow 72 hours before allowing vehicular traffic or chemical cleaning.
10. Full cure in 7 days.

CLEAN UP

Wash all equipment with xylene immediately on completion of application and mixing.

Epo Shield 110

Clear, high gloss, solvent free epoxy top coat system

PRECAUTIONS

- Some individuals may experience a skin reaction to Epo Shield 110. Use appropriate protection equipment. Refer to our Material Safety Data Sheet for further information.
- Do not apply to steel or metal surfaces as corrosion may occur.
- In enclosed areas ventilation should be provided during the coatings curing cycle to allow for adequate curing of the coating.
- Epo Shield 110 is an internal flooring system only.
- Epo Shield 110 will yellow slowly when subjected to direct UV light.
- Discard all material that has exceeded the products recommended pot life or working times.
- Epo Shield 110 is a coating, not a water proofing membrane.
- Do not apply Epo Shield 110 over any existing coating or concrete treatment such as curing compound or release agents. All contaminants must be removed prior to the application of Epo Shield 110.
- Apply Epo Shield 110 between 10°C - 35°C.

Contact the manufacturer if one or more of the following conditions exist:

- The substrate is subject to hydro static pressure or rising damp.
- The substrate is chalky or dusting.
- Ambient or substrate temperatures are below 10°C.
- The finished floor will be subject to chemical attack (including hot chicken fats).

APPLICATION TO COLD SUBSTRATES OR DURING COLD CLIMATES

- Epo Shield 110 cure rates are dramatically reduced when applying to a substrate surface or ambient air temperature below 10°C.
- Applying Epo Shield 110 to cold substrates or during cold climates can cause amine blush, resulting in an oily residue and/or areas of uncured tacky discolouration.
- If the above occurs or any other surface contamination or discolouration appears on the coating, the Epo Shield 110 should be allowed to cure and then washed with fresh clean water, methylated spirits or xylene depending on the severity of the amine blush.
- Ensure total removal of all contamination prior to the application of any further product.
- Any failure to follow the above procedure will result in delamination between coats.
- Strictly follow all mixing instructions.
- Allow mixed product to sit for five minutes to assist in accelerating the drying reaction.
- Do not apply thin coats as rapid moisture loss will arrest or slow the drying reaction.
- Always provide adequate ventilation during the curing cycle.

STORAGE

- Keep Epo Shield 110 stored in a dry area, away from direct sunlight & frost.
- Store between 10°C & 30°C.
- Epo Shield 110 has a shelf life of 12 months in an unopened container.
- Ensure partly used drums are correctly sealed.

FIRE

Product is non-flammable and poses no fire risk.

Epo Shield 110

Clear, high gloss, solvent free epoxy top coat system

SAFETY PRECAUTIONS

- Wear appropriate protective equipment, including clothing, gloves, appropriate respiratory mask and goggles.
- If poisoning occurs, contact doctor or Poisons Information Centre.
- If contact with skin occurs, remove contaminated clothing and thoroughly wash skin.
- If swallowed do not induce vomiting, give a glass of water.
- If in eyes, hold eyes open and flood with water for at least 15 minutes then see doctor immediately.
- For further information refer to the relevant Material Safety Data Sheet.

WARRANTIES

CONPELL offers warranties when their systems are applied by accredited applicators. Please contact manufacturer for further information.

IMPORTANT INFORMATION

The information and recommendations relating to Epo Shield 110 are given based on current knowledge and experience. Due to variances in material substrates and site conditions no warranties implied by law or, fit to purpose of the product can be implied. We accept no responsibility for loss or injury due to the incorrect handling or improper use of the product, limiting the cost of our liability to the replacement product cost only. Always refer to current Product Technical Data Sheets.

CONPELL

Head Office: PO Box 2168

Ph: 1300 966 118

Brisbane Sales: 0450 040 848

Nerang DC, Qld 4211

Fax: 1300 922 001

National Sales: 0433 400 220

Email: info@conpell.com Web: www.conpell.com