

Pen Shield AC25 Matt

Solvent based Acrylic Matt sealer

DESCRIPTION

Pen-Shield AC25 Matt is a concrete dust proofer and sealer that makes concrete more easily cleaned and resistant to penetration from oils and other liquids and is ideal for external driveways, light industrial floors, warehousing and car parking areas.

Pen Shield AC25 Matt has excellent adhesion to cementitious based products.

PRODUCT FEATURES & BENEFITS

- Excellent adhesion
- Easy to apply with brush, roller or spray application
- Comes ready to use
- UV stable
- Easy to re-coat
- Suitable for external use
- Cost effective

TYPICAL APPLICATIONS

Pen-Shield AC25 Matt can be used in a variety of applications including Driveways, Warehouse floors, Light industrial floors, Urban Landscaping, Patios and Entertaining areas.

APPLICATION RATES

Pen Shield AC25 Matt is designed for a two coat application, total application rates are typically between 2-3m² per litre depending on the substrate. (Contact manufacturer for more details).

PACK SIZES

Pen-Shield AC25 Matt is available in 20ltr containers.

PERFORMANCE PROPERTIES

COLOUR	CLEAR, COLOURLESS LIQUID
FINISH	MAt t
VOLUME SOLIDS	APPROX 25%
Pot LIFE	12 MONt HS IN FULLY SEALED DRUM
DRYING t IME	t TOUCH DRY 2 HOURS @ 25°C
RECOAt t IME	2 HOURS At 25°C
FULL CURE	7 DAYS @ 25°C

Pen Shield AC25 Matt

Solvent based Acrylic Matt sealer

SURFACE PREPARATION

The concrete substrate must be cured in accordance with relevant standards, the concrete must be cured for a minimum of 7 days prior to the application of Pen Shield AC25 Matt.

All concrete must be clean, dry and free of all contaminants prior to the application of Pen Shield AC25 Matt, this includes curing compounds and release agents.

As Pen Shield AC25 Matt is a relatively thin coating the substrate must be a fine texture, any surface irregularities will cause extra wear on the coating.

APPLICATION OF PRODUCT

Existing Concrete

All surface contaminants must be removed, once removed clean the concrete surface using a universal degreaser, making sure to remove all oil stains (strictly following manufacturers instructions), then ensure all traces of the degreaser is thoroughly washed away using a high pressure water blaster.

Wash down the concrete with clean water then apply a mild acid wash (one part citric acid to 10 parts water) to the entire area. Leave the acid wash solution on the surface for five minutes then remove the acid wash solution using clean water and a high – pressure water blaster.

Scrub the surface with Xylene (to soften the surface) prior to application of Pen Shield AC25 Matt.

If the existing sealer is unknown, apply a small sample of Pen Shield AC25 Matt to a small area and observe for two-three weeks, evaluate whether the sealers are bonding satisfactorily. If the existing sealer is unsound, it will need to be completely removed, all surfaces must be thoroughly dry before applying the sealer.

Over New Concrete

All surface contaminants must be removed, once removed clean the concrete surface using a universal degreaser, making sure to remove all oil stains (strictly following manufacturers instructions), then ensure all traces of the degreaser is thoroughly washed away using a high pressure water blaster.

Where efflorescence or laitance are present, clean the surface using a mild acid wash may be required (one part hydrochloric acid to 20 parts water). Leave the acid wash solution on the surface for five minutes then remove the acid wash solution using clean water and a high – pressure water blaster. **DO NOT USE ACID SOLUTION ON COLOURED CONCRETE.**

All concrete surfaces must be thoroughly dry before applying the sealer.

APPLICATION

FIRST COAT

1. Thin the first coat with xylene up to 20%.
2. Apply Pen Shield AC25 Matt using a quality solvent resistant broom head, short napped roller or metal low-pressure sprayer.
3. Allow a minimum of two hours between coats, for best results allow 24 hours before applying the second coat.

Pen Shield AC25 Matt

Solvent based Acrylic Matt sealer

SECOND COAT

Stir thoroughly and apply as above, however thinning is not required. Apply the second coat at right angles to the previous coat.

CLEAN UP

Wash all equipment thoroughly with xylene.

CURING

Curing time depends on the temperature. Pen Shield AC25 Matt is usually touch-dry in 20 minutes at 25°C.

The concrete can usually be walked on after 24 hours. Allow seven days before using vehicular traffic or cleaning with chemicals.

COATING LIFESPAN

The expected lifespan of the coating will be effected by the location, weathering and traffic the concrete is subjected to. In exposed, heavy traffic areas, re-coating may be necessary after 18 months. In light use areas, protected from adverse weather conditions the coating will last longer.

TRACTION ENHANCEMENT

The final texture must be through the texture of the concrete surface, care must be taken when sealing concrete to ensure that the surface texture has sufficient profile to provide adequate traction.

If added traction is required, crushed glass should be broad cast between coats of Pen Shield AC25 Matt, this however is only a short term fix as the crushed glass will break down with regular traffic.

PRECAUTIONS

- Do not apply to damp surfaces.
- Protect surrounding areas from overspray, buildings, plants, drains etc.
- Wear suitable protective wear, solvent resistant gloves, protective clothing, safety goggles and organic vapour respirator.
- Protect sealed surface from moisture for a minimum of 6 hours.
- Avoid applying Pen Shield AC25 Matt in windy conditions.
- Apply Pen Shield AC25 Matt between 10°C - 35°C.

STORAGE

Pen Shield AC25 Matt

Solvent based Acrylic Matt sealer

- Keep Pen Shield AC25 Matt stored in a dry area, away from direct sunlight & frost.
- Store between 10°C & 30°C.
- Pen Shield AC25 Matt has a shelf life of 12 months in an unopened container.
- Ensure partly used drums are correctly sealed.

FIRE

Pen Shield AC25 Matt is flammable.

SAFETY PRECAUTIONS

- Wear appropriate protective equipment, including clothing, gloves, appropriate respiratory mask and goggles.
- If poisoning occurs, contact doctor or Poisons Information Centre.
- If contact with skin occurs, remove contaminated clothing and thoroughly wash skin.
- If swallowed do not induce vomiting, give a glass of water.
- If in eyes, hold eyes open and flood with water for at least 15 minutes then see doctor immediately.
- For further information refer to the relevant Material Safety Data Sheet.

IMPORTANT INFORMATION

The information and recommendations relating to Pen Shield AC25 Matt are given based on current knowledge and experience. Due to variances in material substrates and site conditions no warranties implied by law or fit to purpose of the product can be implied. We accept no responsibility for loss or injury due to the incorrect handling or improper use of the product, limiting the cost of our liability to the replacement product cost only. Always refer to current Product technical Data Sheets.

CONPELL

Head Office: PO Box 4252

Ph: 1300 966 118

Brisbane Sales: 0450 040 848

Loganholme DC, Qld 4129

Fax: 1300 922 001

National Sales: 0433 400 220

Email: info@conpell.com Web: www.conpell.com